

AMENDMENTS TO THE CLAIMS

Claim 1 (Currently Amended): A nematic liquid crystal composition comprising

at least one compound selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1) and (IB-3), the total content being from 10 to 40% by mass, at least one compound selected from the group of compounds represented by the general formulas (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID), the total content being from 10 to 70% by mass, the content of the compound represented by the general formula (IIC), (IIC-3), (IIC-7), (IIC-9) and (IIC-10) being from 10 to 40% by mass, the total content of the compounds selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIC), (IIC-3), (IIC-7), (IIC-9) and (IIC-10) being from 45 to 70% by mass,




















the total content of at least one compound selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID) being from 35 to 80% by mass, and


a compound represented by the general formula (III) in the content of 20 to 65% by mass,

wherein a dielectric constant anisotropy is within a range from -12 to -3,

a nematic phase-isotropic liquid phase transition temperature (T_{N-I}) is within a range from 80 to 120°C, and

a viscosity is 45 mPa·s or less:





wherein R^1 , R^3 , R^5 , R^7 , R^9 , R^{11} , R^{12} , R^{13} and R^{14} each independently represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly;


R^2 , R^4 , R^6 , R^8 and R^{10} each independently represents an alkyl group having 1 to 10 carbon atoms, or an alkenyl group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups, which are present in said alkyl group, ~~or said alkoxy group~~, said alkenyl group ~~or said alkenyloxy group~~, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly; and

Z^1 to Z^6 and Z^9 to Z^{11} each independently represents a single bond, $-CH_2CH_2-$, $-CH=CH-$, $-CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH_2O-$, $-OCH_2CH_2CH_2-$, $-CH=CHCH_2CH_2-$, $-CH_2CH_2CH=CH-$, $-C\equiv C-$, $-CH_2O-$, $-OCH_2-$, $-CF_2O-$, $-COO-$, or $-OCO-$;

Z^7 and Z^8 each independently represents a single bond, $-CH_2CH_2-$, $-CH=CH-$, $-CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH_2O-$, $-OCH_2CH_2CH_2-$, $-CH=CHCH_2CH_2-$, $-CH_2CH_2CH=CH-$, $-C\equiv C-$, $-CH_2O-$, or $-OCH_2-$; l and m represents 0 or 1;


A represents a trans-1,4-cyclohexylene group or a 1,4-phenylene group; and


B, C and D each independently represents a trans-1,4-cyclohexylene group, a 1,4-phenylene group, or a trans-1,4-cyclohexenylene group, ~~and~~



wherein R¹ and R³ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, CO- or COO-, while O atoms do not bond with each other directly; and R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 2 (Currently Amended): A nematic liquid crystal composition comprising at least one compound selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1) and (IB-3), the total content being from 25 to 60% by mass, at least one compound selected from the group of compounds represented by the general formulas (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID), the total content being from 10 to 70% by mass, the total content of the compounds selected from the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3) and (IIB-5), being from 35 to 65% by mass, the total content of at least one compound selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID) being from 35 to 80% by mass, and a compound represented by the general formula (III) in the content of 20 ~~35~~ to 65% by mass, wherein a dielectric constant anisotropy is within a range from -12 to -3, a nematic phase-isotropic liquid phase transition temperature (T_{N-I}) is within a range from 80 to 120°C, and a viscosity is 45 mPa·s or less:






wherein R^1 , R^3 , R^5 , R^7 , R^9 , R^{11} , R^{12} , R^{13} and R^{14} each independently represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly;

R^2 , R^4 , R^6 , R^8 and R^{10} each independently represents an alkyl group having 1 to 10 carbon atoms, or an alkenyl group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups,

which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly; and

Z^1 to Z^6 and Z^9 to Z^{11} each independently represents a single bond, -CH₂CH₂-, -CH=CH-, -CH₂CH₂CH₂CH₂-, -CH₂CH₂CH₂O-, -OCH₂CH₂CH₂-, -CH=CHCH₂CH₂-, -CH₂CH₂CH=CH-, -C≡C-, -CH₂O-, -OCH₂-, -CF₂O-, -COO-, or -OCO-; Z^7 and Z^8 each independently represents a single bond, -CH₂CH₂-, -CH=CH-, -CH₂CH₂CH₂CH₂-, -CH₂CH₂CH₂O-, -OCH₂CH₂CH₂-, -CH=CHCH₂CH₂-, -CH₂CH₂CH=CH-, -C≡C-, -CH₂O-, or -OCH₂-; l and m represent 0 or 1; A represents a trans-1,4-cyclohexylene group or a 1,4-phenylene group; and B, C and D each independently represents a trans-1,4-cyclohexylene group, a 1,4-phenylene group, or a trans-1,4-cyclohexenylene group, and























wherein R¹ and R³ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, CO or COO-, while O atoms do not bond with each other directly; and

R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 3 (Currently Amended): A nematic liquid crystal composition comprising at least one compound

selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1) and (IB-3), the total content being from 10 ~~20~~ to 70% by mass, at least one compound selected from the group of compounds represented by the general formulas (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID), the total content being from 10 to 70% by mass, the total content of the compounds selected from the group of compounds selected from the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3) and (IIB-5), being from 20 to 60% by mass, the total content of the compounds selected from the group of compounds represented by the general formulas (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID) being from 30 to 60% by mass, the total content of the compounds selected from the group of compounds represented by the general formulas (IA), (IA-1), (IA-3), (IB), (IB-1), (IB-3), (IIA), (IIA-1), (IIA-3), (IIA-5), (IIB), (IIB-1), (IIB-3), (IIB-5), (IIC), (IIC-3), (IIC-7), (IIC-9), (IIC-10) and (IID) being from 35 ~~70~~ to 80% by mass, and a compound represented by the general formula (III) in the content of 20 to 65% by mass, wherein a dielectric constant anisotropy is within a range from -12 to -3, a nematic phase-isotropic liquid phase transition temperature (T_{N-I}) is within a range from 80 to 120°C, and a viscosity is 45 mPa·s or less:






wherein R^1 , R^3 , R^5 , R^7 , R^9 , R^{11} , R^{12} , R^{13} and R^{14} each independently represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly;

R^2 , R^4 , R^6 , R^8 and R^{10} each independently represents an alkyl group having 1 to 10 carbon atoms, or an alkenyl group having 2 to 10 carbon atoms, and one, or two or more CH_2 groups, which are present in said alkyl group, ~~or said alkoxy group~~, said alkenyl group ~~or said alkenyloxy group~~, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly; and


Z^1 to Z^6 and Z^9 to Z^{11} each independently represents a single bond, $-CH_2CH_2-$, $-CH=CH-$, $-CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH_2O-$, $-OCH_2CH_2CH_2-$, $-CH=CHCH_2CH_2-$, $-CH_2CH_2CH=CH-$, $-C\equiv C-$, $-CH_2O-$, $-OCH_2-$, $-CF_2O-$, $-COO-$, or $-OCO-$; Z^7 and Z^8 each independently represents a single bond, $-CH_2CH_2-$, $-CH=CH-$, $-CH_2CH_2CH_2CH_2-$, $-CH_2CH_2CH_2O-$, $-OCH_2CH_2CH_2-$, $-CH=CHCH_2CH_2-$, $-CH_2CH_2CH=CH-$, $-C\equiv C-$, $-CH_2O-$, or $-OCH_2-$; l and m represent 0 or 1; A represents a trans-1,4-cyclohexylene group or a 1,4-phenylene group; and B, C and D each independently represents a trans-1,4-cyclohexylene group, a 1,4-phenylene group, or a trans-1,4-cyclohexenylene group, ~~and~~



wherein R^1 and R^3 represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly; and

R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 4 (Currently Amended): The nematic liquid crystal composition according to claim 1, wherein the compound represented by the general formula (IA) comprises compounds represented by the general formulas (IA-2) or (IA-4), and the compound represented by the general formula (IB) comprises compounds represented by the general formulas (IB-2) or (IB-4):



wherein R¹ and R³ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly; and

R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 5 (Currently Amended): The nematic liquid crystal composition according to claim 1, wherein the compound represented by the general formula (IIA) comprises compounds represented by the general formulas (IIA-2), (IIA-4) or (IIA-6), and the compound represented by the general formula (IIB) comprises compounds represented by the general formulas (IIB-2), (IIB-4) or (IIB-6):




wherein R^5 and R^7 represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH_2 groups, which are present in said alkyl

group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, and each substituent preferably represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms, and the alkenyl group is particularly preferably a vinyl group, 1-propenyl group, or a 3-butenyl group, and

R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 6 (Currently Amended): The nematic liquid crystal composition according to claim 1, wherein the compound represented by the general formula (IIC) comprises compounds represented by the general formulas (IIC-1), (IIC-2), (IIC-4), (IIC-5), (IIC-6) or (IIC-8):



wherein R^9 represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH_2 groups, which are present in said alkyl group, said


alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$, or $-COO-$, while O atoms do not bond with each other directly, and R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 7 (Currently Amended): The nematic liquid crystal composition according to claim 1, wherein the compound represented by the general formula (IID) comprises compounds represented by the general formulas (IID-1) to (IID-3):



wherein R^{11} represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly, ~~the substituent preferably represents an alkyl group having 1 to 5 carbon atoms, or an alkenyl group having 2 to 5 carbon atoms, and the alkenyl group is particularly preferably a vinyl group, a 1-propenyl group, or a 3-butenyl group,~~ and R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 8 (Currently Amended): The nematic liquid crystal composition according to claim 1, wherein the compound represented by the general formula (III) comprises compounds represented by the general formulas (III-1) to (III-22):



wherein R^{13} and R^{14} represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atom, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH_2 groups, which are present in said alkyl

group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, each substituent independently represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms, ~~preferably, and the alkenyl group is particularly preferably a vinyl group, a 1-propenyl group, or a 3-butenyl group.~~

Claim 9-11: (Canceled)

Claim 12 (Previously Presented): The nematic liquid crystal composition according to claim 4, wherein the dielectric constant anisotropy is within a range from -12 to -6,

the nematic phase-isotropic liquid phase transition temperature (T_{N-I}) is within a range from 80 to 120°C,


the refractive index anisotropy is within a range from 0.07 to 0.15, and

the viscosity is 45 mPa·s or less.

Claim 13 (Previously Presented): A liquid crystal display device for active matrix display, using the nematic liquid crystal composition according to claim 1.

Claim 14 (Previously Presented): A liquid crystal display device for VA mode, IPS mode or ECB mode, using the nematic liquid crystal composition according to claim 1.


Claim 15 (Currently Amended): The nematic liquid crystal composition according to claim 2, wherein the compound represented by the general formula (IA) comprises compounds represented by the general formulas (IA-2) or (IA-4), and the compound represented by the general formula (IB) comprises compounds represented by the general formulas (IB-2) or (IB-4):



wherein R¹ and R³ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly; and

R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 16 (Currently Amended): The nematic liquid crystal composition according to claim 3, wherein the compound represented by the general formula (IA) comprises compounds represented by the general formulas (IA-2) or (IA-4), and the compound represented by the general formula (IB) comprises compounds represented by the general formulas (IB-2) or (IB-4):



wherein R^1 and R^3 represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-\text{O}-$, $-\text{CO}-$ or $-\text{COO}-$, while O atoms do not bond with each other directly; and

R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 17 (Currently Amended): The nematic liquid crystal composition according to claim 2, wherein the compound represented by the general formula (IIA) comprises compounds represented by the general formulas (IIA-2), (IIA-4) or (IIA-6), and the compound represented by the general formula (IIB) comprises compounds represented by the general formulas (IIB-2), (IIB-4) or (IIB-6):



wherein R^5 and R^7 represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH_2 groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with $-O-$, $-CO-$ or $-COO-$, while O atoms do not bond with each other directly, and each substituent preferably represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms, and the alkenyl group is particularly preferably a vinyl group, 1-propenyl group, or a 3-butenyl group, and

R^{15} represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 18 (Currently Amended): The nematic liquid crystal composition according to claim 3, wherein the compound represented by the general formula (IIA) comprises compounds represented by the general formulas (IIA-2), (IIA-4) or (IIA-6), and the compound represented by the general formula (IIB) comprises compounds represented by the general formulas (IIB-2), (IIB-4) or (IIB-6):




wherein R⁵ and R⁷ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy

group having 2 to 10 carbon atoms, one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, ~~and each substituent preferably represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms, and the alkenyl group is particularly preferably a vinyl group, 1-propenyl group, or a 3-butenyl group, and~~

R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 19 (Currently Amended): The nematic liquid crystal composition according to claim 2, wherein the compound represented by the general formula (IIC) comprises compounds represented by the general formulas (IIC-1), (IIC-2), (IIC-4), (IIC-5), (IIC-6) or (IIC-8):



wherein R⁹ represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO-,


or -COO-, while O atoms do not bond with each other directly, and R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 20 (Currently Amended): The nematic liquid crystal composition according to claim 2, wherein the compound represented by the general formula (IID) comprises compounds represented by the general formulas (IID-1) to (IID-3):



wherein R¹¹ represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, ~~the substituent preferably represents an alkyl group having 1 to 5 carbon atoms, or an alkenyl group having 2 to 5 carbon atoms, and the alkenyl group is particularly preferably a vinyl group, a 1-propenyl group, or a 3-butenyl group,~~ and R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.


Claim 21 (Currently Amended): The nematic liquid crystal composition according to claim 2, wherein the compound represented by the general formula (III) comprises compounds represented by the general formulas (III-1) to (III-22):



wherein R^{13} and R^{14} represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atom, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH_2 groups, which are present in said alkyl


group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, each substituent independently represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms, ~~preferably, and the alkenyl group is particularly preferably a vinyl group, a 1-propenyl group, or a 3-butenyl group.~~

Claim 22 (New): The nematic liquid crystal composition according to claim 3, wherein the compound represented by the general formula (IIC) comprises compounds represented by the general formulas (IIC-1), (IIC-2), (IIC-4), (IIC-5), (IIC-6) or (IIC-8):




wherein R⁹ represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, and one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO-, or -COO-, while O atoms do not bond with each other directly, and R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 23 (New): The nematic liquid crystal composition according to claim 3, wherein the compound represented by the general formula (IID) comprises compounds represented by the general formulas (IID-1) to (IID-3):



wherein R¹¹ represents an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atoms, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH₂ groups, which are present in said alkyl group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, and R¹⁵ represents an alkyl group having 1 to 10 carbon atoms or an alkenyl group having 2 to 10 carbon atoms.

Claim 24 (New): The nematic liquid crystal composition according to claim 3, wherein the compound represented by the general formula (III) comprises compounds represented by the general formulas (III-1) to (III-22):



wherein R¹³ and R¹⁴ represent an alkyl group having 1 to 10 carbon atoms, an alkoxy group having 1 to 10 carbon atoms, an alkenyl group having 2 to 10 carbon atom, or an alkenyloxy group having 2 to 10 carbon atoms, one or more CH₂ groups, which are present in said alkyl

group, said alkoxy group, said alkenyl group or said alkenyloxy group, may be substituted with -O-, -CO- or -COO-, while O atoms do not bond with each other directly, each substituent independently represents an alkyl group having 1 to 5 carbon atoms or an alkenyl group having 2 to 5 carbon atoms.